UPM Raflatac Technical Information

20.01.2012 ENG 186

ADHESIVE Permanent Type Composition Use	RP 51 RP5X (sales code) General purpose strong permanent. Acrylic, water borne. Good adhesion to all normal substrates, including non-polar surfaces, films, and corrugated board. Good low temperature performance.		
Typical technical values			
Tack min	14	Ν	FTM 9
Shear min	1.0	h	FTM 8
PE-looptack min	10	Ν	modified FTM 9
Labelling temperature min	0	°C	
Service temperature min	-20	С°	
Service temperature max	80	°C	
Limitations	Not recommended for labelling highly curved surfaces.		
Approvals	The research centre ISEGA has given the adhesive approval for direct contact with dry and moist non-fatty foods.		
Shelf life	From the date of manufacture 4 years in +20°C and RH 50%.		
Warranty	Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. This publication replaces all previous versions. All information is subject to change without notice.		

